

Tecnical Data Sheet

PC REPELLETIZE C1

WSM23120802

Physical Properties	Test Method*	Unit	Typical Values
Specific Gravity	ASTM D-792	-	1,20
Melt Flow Index (1.2kg-300C)	ASTM D-1238	g/10 min	19

Mechanical Properties	Test Method*	Unit	Typical Values
Tensile Strength	ASTM D-638	kgf/cm ²	830
Tensile Elongation	ASTM D-638	%	4,5
Flexural Strength	ASTM D-790	kgf/cm ²	1140
Flexural Modulus	ASTM D-790	kgf/cm ²	34700
Flexural Elongation	ASTM D-790	%	19,2

Impact	Test Method*	Unit	Typical Values
Izod Impact Strength (notched 23°C , 3mm)	ASTM D-256	(Kg-cm/cm)	13

PROCESSING GUIDE

Parameter		
Drying Temperature	100 - 120	°C
Drying Time	4	hour
Mold Temperature	80 - 110	°C
Processing Melt Temperature	270 - 310	°C

updated on 11/12/2023

* ASTM testing conditions as indicated ; the test result are provided for guidance purpose only and do not reflect result that may be obtained under different conditions. No warranty with regard to the product quality, safety or performance is intended or otherwise implied by the publication of these data. The producer and the distributors assume no responsibility or liability for any occurrence related to the storage, handling, processing, use or disposal or to the final use of this product; such responsibility and all liability are exclusively borne by the and user.